



Bona SuperSport Pure HD



Resilient Floor Coating

- ✓ Tough PUR for resilient sport floors
- ✓ Rapid drying for minimal downtime
- ✓ Optimal application and levelling
- ✓ EN 14904:2006 Compliant



X-Matt Matt Silkmat Gloss

2-component / Zweisamponentig
2-componente / Bicomponent



4.55 L

Waterborne PUR coating for sport flooring
Wasserbasierte PUR Versiegelung für elastische Bodenbeläge
Couche de protection pure en phase aqueuse pour les sols élastiques
Barraiz acabado al agua de PU para suelos elásticos

Bona[®]

Bona SuperSport Pure HD

SPORTIVE SYSTEM – THE FOUNDATION FOR A GREAT GAME



Bona SuperSport Pure HD

The foundation for a great game

Bona SuperSport Pure HD is a hard-elastic and hardwearing PUR coating for the treatment of resilient floor coverings in sport halls. It serves as a long-term surface protection while restoring appearance, safe friction and simplifying routine maintenance. Bona SuperSport Pure HD consists of a waterborne, clear, non-yellowing formula.

APPLICATION

Apply Bona SuperSport Pure HD using a Bona Roller (11 mm pile)

KEY BENEFITS

- Tough PUR protection for resilient sport floors
- Rapid drying for minimal downtime. Back on the floor in 12 hours*
- Optimal application and levelling properties
- Compliant to EN 14904:2006 (Indoor Sport Surfaces)

TECHNICAL DATA

Type of coating:	2-component waterborne polyurethane topcoat
Solids content:	Approx. 45%
VOC:	<1%
Sheen (at 60°):	20%
Mixing ratio:	1 part Bona Pure Hardener to 10 parts Bona Pure
Pot life:	max. 2 hours at 20°C (shorter if warmer)
Dilution:	Do not dilute

TECHNICAL DATA

Drying time, until:	- Overcoatable: approx. 2-4 hours* - Light use: 12 hours* - Full hardness: approx. 5-7 days* <small>*under normal climate conditions, 20°C/60% R.H.</small>
Application tools:	Bona Polyester Roller (11 mm pile)
Application rate:	8-10 m ² /litre (120-100g/m ²) per coat
Safety:	Coating: Unclassified Hardener: Classified (see Safety Data Sheet)
Cleaning:	Wipe tools free from residual material before cleaning with a minimum of water. Dried material can be removed with acetone
Shelf life:	1 year from date of production in unopened original container
Storage/transport:	The temperature must not fall below +5°C or exceed +25°C during storage and transport
Disposal:	Wastes and emptied containers should be handled in accordance with local regulations
Pack size:	3 x 5 litres incl. hardener
Certification:	Compliant to EN 14904:2006 and DIN 18032:2; indoor sports EC1RPLUS; Very low emission and indoor pollution GreenGuard; Indoor air quality EN 71-3; Safe for application on children's toys